

## SEPIOLITA 30/60 / SEPIOLITE 30/60

### CARACTERÍSTICAS FÍSICO-QUÍMICAS / PHYSICO- CHEMICAL PROPERTIES

Tolerancia/Tolerance

|                                                          |         |          |
|----------------------------------------------------------|---------|----------|
| DENSIDAD APARENTE / BULK DENSITY (BS 1460).....          | 650 g/l | < 720g/l |
| ABSORCIÓN DE AGUA / WATER ABSORPTION (WESTINGHOUSE)..... | 145 %   | >110%    |
| ABSORCIÓN DE ACEITE / OIL ABSORPTION (WESTINGHOUSE)..... | 80 %    | >65%     |
| pH (NF T 30-035).....                                    | 8,5     | +/- 1,0  |

### GRANULOMETRÍA / PARTICLE SIZE DISTRIBUTION

|                      |         |                   |       |
|----------------------|---------|-------------------|-------|
| > 0,85 mm .....      | < 1 %   | Mesh >20 .....    | < 1%  |
| 0,85 – 0,25 mm.....  | > 96 %  | Mesh 20-60.....   | > 96% |
| 0,25 – 0,15 mm ..... | < 2 %   | Mesh 60-100 ..... | < 2%  |
| < 0,15 mm.....       | < 1,5 % | Mesh <100 .....   | <1,5% |

### COMPOSICIÓN MINERALÓGICA / MINERALOGY COMPOSITION

|                                       |     |      |
|---------------------------------------|-----|------|
| SEPIOLITA (DRX)/ SEPIOLITE (XRD)..... | 75% | >65% |
|---------------------------------------|-----|------|